

Vilkyd Alkyd Resins for AC Lacquers

TECHNICAL DATA SUMMARY

We summarise below the alkyd resins in our standard range recommended for use in acid cured wood finishes. Full information on all products is given on the individual technical data sheet.

Vilkyd Ref No.	% Non-Volatile Content	Solvent	Viscosity @ 25°C Poise	% Non-Volatile Content @ 2 Poise	% Fatty Acid	Fatty Acid/Oil Type	Esterifying Agent	Principal Uses
202H80	80	Butyl acetate	15-25	69	49	Linoleic Rich	Penta	High solids finishes with good stability, durability and non-yellowing properties
205X60	60	Xylene	60-100	44	35	Linoleic Rich	Mixed	Versatile resin for A/C laquers, stoving or air dry finishes.
209FY85	85	IMS/ Methoxy propanpol	30-50	87	50	Linoleic Rich	Penta	Fast curing wood finishes with excellent stability are required

RESINS WITHOUT RIVAL

This information is offered in good faith but without guarantee as to the suitability of the product or the suggested uses, nor can it be assumed that the uses will not infringe any patents.



RESINS

Vil Resins Ltd The Valley Bolton BL2 2DT
Tel: +44(0)1204 388800 Fax: +44(0)1204 362775
Website: www.vilresins.com Email: enquiries@vilresins.co.uk