

Vilkyd Resins for low VOC Coatings

TECHNICAL DATA SUMMARY

ALKYD RESINS

Vilkyd Ref No.	% Non-Volatile Content	Solvent	Viscosity @ 25°C Poise	% Non-Volatile @ 2 Poise	% Fatty Acid	Fatty Acid Type	Esterifying Alcohol	Principal Uses
157X80	80	Xylene	50-80	55	43	Linoleic Rich	Mixed	Copolymer alkyd for best through drying properties
188X75	75	Xylene	60-90	56	36	Linoleic Rich	Pentaerythritol	Compliant air drying and stoving finishes with excellent water spot resistance
211X80	80	Xylene	80-120	56	64	Linoleic Rich	Pentaerythritol	High Solids Coatings
251	100	-	15-25	80	74	Linoleic Rich	Pentaerythritol	Pigment dispersion
254	100	-	60-90	67	74	Mixed	Pentaerythritol	Addition to long oil alkyds to help achieve compliancy
258	100	-	30-50	75	78	Linseed	Pentaerythritol	High Solids coatings with excellent pigment wetting

RESINS WITHOUT RIVAL

This information is offered in good faith but without guarantee as to the suitability of the product or the suggested uses, nor can it be assumed that the uses will not infringe any patents.



RESINS

Vil Resins Ltd The Valley Bolton BL2 2DT
Tel: +44(0)1204 388800 Fax: +44(0)1204 362775
Website: www.vilresins.com Email: enquiries@vilresins.co.uk